

17025 SO. MAIN ST. GARDENA, CA 90248 800.572.9029 13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 stepstoneprecast.com

## **MATERIAL PRODUCT DATA SHEET**

Product Name

Dekstone®

# Manufacturer

Stepstone, LLC 17025 So. Main St. Gardena, CA 90248 
 Phone
 310-327-7474

 Fax
 310-217-1424

 Toll free
 800-572-9029

## **Product Description**

Stepstone has produced high quality precast concrete since 1963. Dekstone<sup>®</sup> is precast concrete pavers developed to be used as an option to a wood decking surface. Dekstone<sup>®</sup> is reinforced with zinc plated welded wire mesh, with 3/8" threaded inserts for attachment. Dekstone<sup>®</sup> is designed for use in commercial and residential applications.

## **Composition & Materials**

Dekstone® is hand-made, wet-cast from 5000 PSI hard rock concrete using Type III cement.

### Sizes

Dekstone<sup>®</sup> is available in standard 23-7/8"x23-7/8"x2".

## Finishes

Dekstone® available finishes include: Sonorastone® slate finish, light, medium, or heavy sandblast

## Colors

Dekstone<sup>®</sup> is available in 19 standard colors: Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble and Porcelain; custom colors are available upon request.

## **Technical Data**

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM) ASTM C33 - Standard Specification for Concrete Aggregates ASTM C39 - Concrete Compressive Strength ASTM C150 - Standard Specification for Portland Cement ASTM C642 - Water Absorption, Density, Voids in Hardened Concrete ASTM C666 - Rapid Freeze/Thaw Resistance of Concrete ASTM C979 - Pigments for Integrally Colored Concrete ASTM C1028 - Coefficient of Friction

## **Physical/Chemical Properties**

Dekstone<sup>®</sup> weight is 22 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8'' from standard dimensions. No unit will differ more than +/- 1/8'' from the approved samples. Test reports are available upon request. Concrete is non-combustible.