



17025 SO. MAIN ST. GARDENA, CA 90248 | 800.572.9029
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | stepstoneprecast.com

MATERIAL PRODUCT DATA SHEET

Product Name

Open Riser Steptread

Manufacturer

Stepstone, LLC
17025 So. Main St.
Gardena, CA 90248

Phone 310-327-7474
Fax 310-217-1424
Toll free 800-572-9029

Product Description

Stepstone has produced high quality pre-cast concrete since 1963. Open Riser Steptreads are reinforced, engineered, pre-cast concrete stairtreads that come in many standard sizes. All Open Riser Steptreads are reinforced with zinc plated welded wire mesh. Open Riser Steptreads are designed for use in commercial and residential applications.

Composition & Materials

Open Riser Steptreads are hand-made, wet-cast from 5000 PSI hard rock concrete using Type III cement.

Sizes

Open Riser Steptreads are available in standard sizes ranging 11"-12" deep, 36"-48" long and 2½" thick. Custom sizes available upon request.

Finishes

Open Riser Steptread available finishes include: Exposed aggregate, broom finish, and light, medium, or heavy sandblast. Bullnose, Wedge, and Square edge profiles are available.

Colors

Open Riser Steptreads are available in 12 standard colors: Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble and Porcelain; custom colors are available upon request. Integral detectable warning stripes are available in Black, Brown or White.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)
ASTM C33 - *Standard Specification for Concrete Aggregates*
ASTM C39 - *Concrete Compressive Strength*
ASTM C150 - *Standard Specification for Portland Cement*
ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*
ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*
ASTM C979 - *Pigments for Integrally Colored Concrete*
ASTM C1028 - *Coefficient of Friction*

Physical /Chemical Properties

Open Riser Steptread weight is 2.5 LBS per lineal inch at 12" length. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, LLC for further information

July 2024