



17025 SO. MAIN ST. GARDENA, CA 90248 | 800.572.9029
13238 SO. FIGUEROA ST. LOS ANGELES, CA 90061 | stepstoneprecast.com

MATERIAL PRODUCT DATA SHEET

Product Name

Truncated Dome Paver

Manufacturer

Stepstone, LLC
17025 So. Main St.
Gardena, CA 90248

Phone 310-327-7474
Fax 310-217-1424
Toll free 800-572-9029

Product Description

Stepstone, Inc. has produced high quality pre-cast concrete since 1963. Truncated Dome Pavers are precast, A.D.A. compliant, CBC 11B-705, detectable warning surface pavers that are designed to be used in commercial as well as public works applications. Pavers have an aligned dome pattern.

Composition & Materials

Truncated Dome Pavers are hand-made, wet-cast from 5000 PSI hard rock concrete using Type III cement.

Sizes

Truncated Dome Pavers are available in the standard sizes 11-7/8"x11-7/8"x2", 11-7/8"x11-7/8"x4" and 23-7/8"x23-7/8"x2" and 23-7/8"x35-7/8"x2-1/2".

Finishes

Truncated Dome Pavers available finishes include: Domed stippled finish or light sandblast

Colors

Truncated Dome Pavers are available in 14 standard colors: Federal Yellow, Charcoal, Adobe, Agave, Almond, Brick Red, Cafe Brown, Caramel, French Gray, Granada White, Iceberg Green, Kona, Pebble and Porcelain; custom colors are available upon request.

Technical Data

APPLICABLE STANDARDS: American Society for Testing & Materials (ASTM)

ASTM C33 - *Standard Specification for Concrete Aggregates*

ASTM C39 - *Concrete Compressive Strength*

ASTM C150 - *Standard Specification for Portland Cement*

ASTM C642 - *Water Absorption, Density, Voids in Hardened Concrete*

ASTM C666 - *Rapid Freeze/Thaw Resistance of Concrete*

ASTM C979 - *Pigments for Integrally Colored Concrete*

ASTM C1028 - *Coefficient of Friction*

Physical/Chemical Properties

Truncated Dome Paver weight is 22 LBS per square foot. Water absorption: Not more than 6.0 % average, not more than 7.0 % for any individual unit for standard colors. Unit length, width and height are not more than +/- 1/8" from standard dimensions. No unit will differ more than +/- 1/8" from the approved samples. Test reports are available upon request. Concrete is non-combustible.

Please contact Stepstone, LLC for further information.

July 2024